

## PRODUCT LIST

### Polyamide Type

Product name	Amine Value	viscosity	PHR	solvent	note
D-035	350±30	200 ~ 600	35		Polyamidoamine sealant , construction, mortar use
D-140	385±15	9000 ~ 15000	54		Polyamide adhesives, linings , coatings
D-220	220±20	50000 ~ 70000*	95		Polyamide adhesives, linings , coatings
D-300	300±20	8000 ~ 12000*	66		Polyamide adhesives, linings , coatings
D-310	310±30	2500 ~ 4500	57		Polyamide adhesives, linings , coatings
D-330(K)	330±30	500 ~ 1000	50		Polyamidoamine sealant , construction, mortar use
D-220H-70X	154±14	500 ~ 1300	35~40**	Xylene	Polyamide solution for preservation coating, marine coating, floor coating applications
D-110NX-65	100±20	Z2 ~ Z4***	80**	Xylene/ n- BuOH	Polyamide solution for preservation coating, marine coating, floor coating applications
D-240IX70	135±15	3000 ~ 7000	50**	Xylene/ ISO- butanol	Polyamide adduct High-performance preservation coating, marine coating, floor coating
D-120IX60	125±15	Z1 ~ Z3***	75**	Xylene/ IPA	Polyamide adduct High-performance preservation coating, marine coating, floor coating

\* : Viscosity measurement range 40°C (basic viscosity = 25°C)  
 \*\* : PHR, EEW = 500 (basic PHR, EEW = 190)\*\*\* : Viscosity measurement method = G-Hold