



DNC Co., Ltd.

92, Jwagong -Ri, Jinyeong-Eup, Gimhae -Si,
Gyeongnam, Korea ☎ 621-802

PRODUCT LIST

Modified Amine

Product name	Amine Value	viscosity	PHR	solvent	note
DM-800	375±25	500 ~ 1500	40		Mannich -Base Low temperature curing excellent coating, adhesive, flooring applications
DM-825	375±25	500 ~ 2000	40		Mannich -Base Low temperature curing excellent coating, adhesive, flooring applications
DM-900	260±40	300 ~ 600	60		modified cycloaliphatic amine transparent flooring applications
DM-932	320±20	1000 ~ 1500	50		modified cycloaliphatic amine transparent flooring applications
DM-520	450±50	100 ~ 500	50		modified aliphatic amine Self-leveling flooring, adhesives, castings
DM-760	450±50	500 ~ 1500	45 ~ 50		modified cycloaliphatic amine stone, adhesive use
DM-3100	275±25	1 ~ 100	54		Modified cycloaliphatic amine Excellent chemical resistance, Self-leveling
DM-3200	250±30	500 ~ 1000	58		modified cycloaliphatic amine Excellent chemical resistance, self-leveling
PHR, EEW = 190 Viscosity = 25°C					

The information and statement herein are believed to be reliable, but are not construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of Any information or products referred to herein. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE.